



Subham Oils and Resins Pvt Ltd

Works: Surjopur Ishwaripur, Bolgarh Industrial Estate Kalyani Expressway, Kolkata-700121

Technical Data Sheet

Acrylic Resin 502K 60%

Applications: Auto refinish, PU refinish, Sanding sealer, Wood Coating

Specifications:

Parameters	Standard Results
Non Volatile Matter (%)	60+-2 %
Acid Value (mg KOH/g)	<6
Viscosity in poise at 25°C in BF spindel-28	30-50
Color in Gardner	<1
Hydroxyl Value (on Solid) (mg KOH/gm)	80-90

Delivery Forms:-

In 17-19 kgs Metal barrels with following net weight for following percentages: