



Subham Oils and Resins Pvt Ltd

HO: Astra Tower ASO 301 3rd Floor Kolkata 700135

Technical Data Sheet

AC35 50% (Styrenated Alkyd Resin)

Applications: Recommended for very fast drying high gloss paints

Drying Time:

Touch Dry	5 mins Max
Tack Free	30 mins Max
Hard Dry	240 mins Max

Specifications:

Parameters	Standard Results
Non Volatile Matter (%)	50
Acid Value (mg KOH/g)	<4
Viscosity 30° C in FB4 Seconds	5-25 Poise in 50% Xylene
Color in Gardner	<7

Solubility:

Xylene	Complete Solubility
MTO/LAWS	No Solubility
Turpentine	No Solubility
n-Butyl Acetate	Complete Solubility

Delivery Forms:-

In 17-19 kgs Metal barrels with following net weight for following percentages:

50% in Xylene	200 kgs
---------------	---------