



Office Address: Saltee Plaza, #614, 6th floor, 1, Khudiram Bose Sarani, Mall Road, Beside: ILS Hospital, Nagerbazar, Kolkata 700080
Phone: 9831042772
Email: rupesh@aquafiltration.com



NANO FILTRATION

Product Details

Model	Flow Rate (GPD,m3/d)	NaCl Rejection(%)	MgSO4 Rejection (%)	Diameter/ Length (inch)	Test Conditions
NE8040-HRM	11,000 (41.6)		98.0	8.0 / 40	NE Standard
NE8040-ARM50	7,000 (26.5)		98.0	8.0 / 40	NE Standard
NE8040-ARM70	6,000 (22.7)		98.0	8.0 / 40	NE Standard
NE4040-SRM	1,600 (6.1)		99.5 (Sulfate 99.5)	8.0 / 40	NE Standard
NE8040-SRM	7,500 (28.4)		99.5 (sulfate 99.5)	8.0 / 40	NE Standard
NE8040-40*	12,000 (45.4)	20-40	98.0	8.0 / 40	NE Standard
NE8040-70*	7,000 (26.5)	40-70	98.0	8.0 / 40	NE Standard
NE8040-90*	8,000 (30.3)	85-97	98.0	8.0 / 40	NE Standard
NE4040-HRM	2,300 (8.7)		98.0	4.0 / 40	NE Standard
NE4040-ARM50	1,500 (5.7)		98.0	4.0 / 40	NE Standard
NE4040-ARM70	1,300 (4.9)		98.0	4.0 / 40	NE Standard
NE4040-40*	2,500 (9.5)	20-40	98.0	4.0 / 40	NE Standard
NE4040-70*	1,500 (5.7)	40-70	98.0	4.0 / 40	NE Standard
NE4040-90*	1,700 (6.0)	85-97	98.0	4.0 / 40	NE Standard

NE Standard test conditions: NaCl 2,000 mg/L, Pressure 75 psig, Temperature 25°C, pH 6.5-7.0 Recovery 15%.

MgSO₄ rejection test conditions: MgSO₄ 2,000 mg/L, Pressure 75 psig, Temperature 25°C, pH 6.5-7.0 Recovery 15%

The stated data were obtained after 30 minutes of operation.