



## Subham Oils and Resins Pvt Ltd

HO: Astra Tower, ASO 301, 3<sup>rd</sup> Floor, Action Area IIC, New Town, Kolkata-700161

### **Technical Data Sheet**

#### **AC-25 50% (Styrenated Alkyd Resin)**

**Applications:** Recommended for very fast drying high gloss paints

**Drying Time:**

Touch Dry	5 mins max
Tack Free	30 mins max
Hard Dry	240 mins max

**Specifications:**

Parameters	Standard Results
Non Volatile Matter (%)	50+-2%
Viscosity at 25C	5-25 Poise in 50% xylene
Color in Gardner	<7
Acid Value (mg KOH/g)	<4

**Solubility:**

Xylene	Complete Solubility
MTO/LAWS	No Solubility
Turpentine	Complete Solubility
n-Butyl Acetate	Complete Solubility
Methyl Ethyl Ketone	Complete Solubility

**Delivery Forms:-**

In 17-19 kgs Metal barrels with following net weight for following percentages:

50% in Xylene	200 Kgs
---------------	---------