



Subham Oils and Resins Pvt Ltd

Works: Surjopur Ishwaripur, Bolgarh Industrial Estate Kalyani Expressway, Kolkata-700121

Technical Data Sheet

Acrylic Resin 612K 60%

Applications: Good outdoor durability, excellent flow and levelling, good gloss and hardness

Specifications:

Parameters	Standard Results
Non Volatile Matter (%)	60+-2 %
Acid Value (mg KOH/g)	<10
Viscosity in poise at 25°C in BF spindel-28	25-35
Color in Gardner	<1
Hydroxyl Value (on Solid) (mg KOH/gm)	50-60

Delivery Forms:-

In 17-19 kgs Metal barrels with following net weight for following percentages: